


Angasi



Product Information	STD ANGASI
Size	230 x 110 x 76
Dimensional Category	DW1
# Pack	600
Approximate Unit Weight (kg)	3.1
Approx Pack Weight	1916
Approximate Bricks Per m2	48.5
Mean Unconfined Compressive Strength (MPa)	12
CWA	10
Core/Void Percentage	<30
Durability Class	General Purpose
Potential to Effloresce	Nil to Slight
Liability to Lime Pitting	Nil to Slight
FRL (min) Single leaf unrendered	90

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 3700 is used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Information subject to change without notice. If you require specific or improved product specification, please contact your Sales Representative.



For more information about Midland Brick

A: 260 Kalamunda Road, South Guildford, WA 6055
P: 6313 1000

DISCLAIMER. The information presented herein is supplied in good faith and to the best of our knowledge was correct at the time of preparation. No responsibility can be accepted by Midland Brick, its staff or its agents for any errors or omissions. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, no responsibility can be accepted by Midland Brick, its staff or its agents for any loss or damage caused by any person acting or refraining from action as a result of this information.