


Product Data Sheet

INFORMATION CURRENT AS OF 01/07/2026

Kennedy



Product Information	KENNEDY	1CSE CORED KENNEDY CORED	1CSE SOLID KENNEDY	KENNEDY 190 SNAP
Size	290x90x162			290x90x162
Dimensional Category	DW1			DW1
# Pack	138			138
Approximate Unit Weight (kg)	5.4			5.4
Approx Pack Weight	768			768
Approximate Bricks Per m2	19.4			19.4
Mean Unconfined Compressive Strength (MPa)	>10			>10
CWA	<12			<12
Core/Void Percentage	<35			<35
Durability Class	General Purpose			General Purpose
Potential to Effloresce	Nil-Slight			Nil-Slight
Liability to Lime Pitting	Nil			Nil
FRL (min) Single Leaf unrendered	60			60

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 3700 is used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Information subject to change without notice. If you require specific or improved product specification, please contact your Sales Representative.



For more information about Midland Brick

A: 260 Kalamunda Road, South Guildford, WA 6055
P: 6313 1000

DISCLAIMER. The information presented herein is supplied in good faith and to the best of our knowledge was correct at the time of preparation. No responsibility can be accepted by Midland Brick, its staff or its agents for any errors or omissions. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, no responsibility can be accepted by Midland Brick, its staff or its agents for any loss or damage caused by any person acting or refraining from action as a result of this information.