


Standard Common Paint Grade



Product Information	STD COMMON PAINT GRADE	SOLID STD COMMON PAINT GR
Size	230x110x76	230x110x76
Dimensional Category	DW1	DW1
# Pack	264	264
Approximate Unit Weight (kg)	3.00	3.8
Approx Pack Weight	816	1033
Approximate Bricks Per m2	48.5	48.5
Mean Unconfined Compressive Strength (MPa)	>12	>15
CWA	<10	<10
Core/Void Percentage	<30	-
Durability Class	General Purpose	General Purpose
Potential to Effloresce	Nil-Slight	Slight
Liability to Lime Pitting	Nil-Slight	Slight
FRL (min) Single leaf unrendered	90	90

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 3700 is used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Information subject to change without notice. If you require specific or improved product specification, please



For more information about Midland Brick

A: 260 Kalamunda Road, South Guildford, WA 6055
P: 6313 1000

DISCLAIMER. The information presented herein is supplied in good faith and to the best of our knowledge was correct at the time of preparation. No responsibility can be accepted by Midland Brick, its staff or its agents for any errors or omissions. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, no responsibility can be accepted by Midland Brick, its staff or its agents for any loss or damage caused by any person acting or refraining from action as a result of this information.



contact your Sales Representative.



For more information about Midland Brick

A: 260 Kalamunda Road, South Guildford, WA 6055

P: 6313 1000

DISCLAIMER. The information presented herein is supplied in good faith and to the best of our knowledge was correct at the time of preparation. No responsibility can be accepted by Midland Brick, its staff or its agents for any errors or omissions. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, no responsibility can be accepted by Midland Brick, its staff or its agents for any loss or damage caused by any person acting or refraining from action as a result of this information.